



# TUNGCAST E

## Stick Electrode DIN EN 14700: E21-GF-UM-60-CG

### General characteristics:

Tungcast E is a tube metal filled with medium size fused tungsten carbide developed for manual application. This electrode can be applied by alternating or direct current trouble free once the proper machine setting is obtained.

### Applications:

For hard facing unalloyed and low alloyed steels (cast steels) with a maximum carbon content of 0.5%. Higher carbon content could lead to cracking. For welding on most high alloyed steels after a buffer layer is applied. Also for hard facing tools and machine parts that experience wear in: Mining, Excavation, Well Digging, Road Construction and Deep Drilling.

### Welding Directions:

Depending on the base metal's alloy and the area to be hard faced, a preheating temperature between 350-500°C (662-932°F) is advised. NOTE: Since Tungcast E is a hollow tube metal filled with fused tungsten carbide powder, the lowest amp setting possible should be used when depositing it in order to avoid any damage to the carbides.

**Hardness:** 55 – 58 HRC

### Standard sizes and current settings:

Type	Ø mm	Ø inch	length of rod	Amps	Voltage
3505	3.5 mm	1/8	350 mm	90 A	= + / ?
4005	4.0 mm	5/32	350 mm	110 A	= + / ?
5005	5.0 mm	3/16	350 mm	140 A	= + / ?
6005	6.0 mm	1/4	350 mm	160 A	= + / ?
8005	8.0 mm	5/16 (18")	350/450 mm	200 A	= + / ?

**P O Box 14675, Kenmore 4069, Australia • 7/20 Spine Street, Sumner 4074, Australia**

**Tel: +61 07 3376 4303 • Fax: +61 07 3376 4305**

Email: [info@hardmetalindustries.com.au](mailto:info@hardmetalindustries.com.au)